



Product information

SYNTEKO RETARDER 1670

GENERAL DESCRIPTION

Synteko Retarder is intended to be added to Synteko Classic 1636, 1637, 1646 to delay the solvent evaporation and thereby maintain a reasonable drying time, also at high temperatures.

TECHNICAL DATA

| | |
|----------------------|---|
| Base material | Solvent mixture |
| Solvents | Ethanol and aliphatic diester |
| Density | Approx. 900 kg/m ³ (7.51 lb/gal US) (9,02 lb/gal UK) |
| Flash point | Highly flammable 14°C (57°F) |
| Shelf life | 24 months in unopened container |
| Storage | Not sensitive to freezing |

DIRECTIONS FOR USE

Synteko Classic 1636, 1637 and 1646 can be diluted 5 to 10% with Synteko Retarder. The amount of Retarder is depending on the temperature and local circumstances, e.g. airing and if the area is large or/and open.

Add Synteko Retarder to the finish and mix well before adding the Synteko Hardener 1647. Synteko Retarder must be used in the last coat only.

HEALTH & SAFETY INFORMATION

Detailed information and guidance is provided in our MSDS (Material Safety Data Sheet). The following only represents a selection of important information.

Note: Highly flammable. Keep container tightly closed and in well-ventilated place. Keep away from source of ignition – No smoking. Keep out of reach of children.



Akzo Nobel Decorative Coatings AB
Synteko Floor Finishes
SE-205 17 Malmö, Sweden
Phone: +46 40 355000
www.synteko.com
Email: info@synteko.com



Our information is based on laboratory tests and is considered a guide in connection with choice of product and working method. As your working conditions are beyond our control, we do not assume any responsibility for the results. Our responsibility covers exclusively personal injury and damage to property, which actually have been proved subsequent to faults and defects in one of the products manufactured by us.

Date: 2004-04-15